


ArmorLiner® 24 11.5 OZ GEOMEMBRANE



Certified to
NSF/ANSI/CAN 61

PRODUCT DESCRIPTION

A heavyweight fabric that incorporates a special weave pattern to enhance puncture, flatness, and tear properties. The coating recipe is designed to improve toughness and abrasion resistance for exposed applications up to 10 years.

RECOMMENDED APPLICATIONS

Decorative Ponds, Canal Reservoirs, Containment Liners

PRODUCT DIMENSIONS

Cores 4 inch I.D. or 5 inch I.D. available (10 cm or 13 cm)
Width Up to 150 in (381 cm) (-0, +0.5) as ordered
Length Minimum 250 yds/roll (229 m); up to 1000 yds/roll (914 m)

PRODUCT SPECIFICATIONS

Weave Woven black HDPE scrim
Coating LDPE, 3.5 mil average each side (83 g/m²/side)
Color White, black or other colored coatings available
Weight 11.5 oz/yd² (390 g/m²) ± 5 %

These values are typical data and are not intended as limiting specifications.

PERFORMANCE PROPERTIES

The following data are typical values based on ASTM standard tests. This data should not be considered specification.

Thickness ASTM D1777	Nominal 24 mil (0.60 mm) ± 10%
Grab Tensile (N) ASTM D7004	MD 415 lb (1846) TD 370 lb (1646)
Strip Tensile (N/5cm) ASTM D7003	MD 275 lb/in (2408) TD 235 lb/in (2058)
Tongue Tear—large scale (N) ASTM D5884	MD 120 lb/in (534) TD 115 lb/in (512)
Mullen Burst ASTM D751	640 psi (4416 kPa)
MVTR ASTM E96 Proc. BW	0.17 g/m ² · 24hr (0.024 perms)
Hydraulic Conductivity (Permeability) Calculated from MVTR	6.94 x 10 ⁻¹⁵ cm/s
Hydrostatic Resistance ASTM D751	425 psi (2928 kPa)
Puncture Resistance ASTM D4833	195 lb (867 N)
CBR Static Puncture ASTM D6241	1157 lb (5137 N)
Carbon Black Content ASTM D4218	3 %
Dimensional Stability ASTM D1204	MD -2.7% TD -1.4%
Low Temperature Flex ASTM D2136	MD & TD: Pass @ -65°C (-85°F)
HP-OIT ASTM D5885 (Measured on coating formulation)	1071 minutes
Accelerated UV Weatheringⁱ ASTM D7238	>90% tensile strength retention after 10,000 light hours

MD = Machine Direction. TD = Transverse Direction

ⁱ Q.U.V [A-340 Lamps]; 20 hrs UV @ 75°C; 4 hrs condensation @ 60°C



Certified to
NSF/ANSI/CAN 61

These values are typical data and are not intended as limiting specifications.

While we believe them to be reliable, the statements and information herein are only for general guidance and are not warrants or guarantees for accuracy and completeness. The user must, by test or otherwise, determine suitability for this purpose. There is no warranty of fitness for a particular purpose. Our standard term and conditions of sale apply exclusively to all orders, and all liability for damages of any kind, including consequential, exceeding purchase price is excluded. No one is authorized by us to make oral warranties. We reserve the right to make changes without notice or obligation in our products and publications.