

Stretch Film

HWI (Hand Wrap I)

INTERTAPE POLYMER GROUP® TECHNICAL DATA SHEET

Test	Values (listed by film thickness)	
	Reference Methods	63 gauge 16.0 micron 0.63 mil
Ultimate Tensile MD (psi)	ASTM D882	6985
Ultimate Tensile TD (psi)	ASTM D882	4506
Elongation MD (%)	ASTM D882	472
Elongation TD (%)	ASTM D882	939
Tear Resistance MD (grams and g/mil)	ASTM D1922	74 grams
		118.1 g/mil
Tear Resistance TD (grams and g/mil)	ASTM D1922	576 grams
		914.29 g/mil
Dart Drop (grams and g/mil)	ASTM D1709	52 grams
		82.54 g/mil
Pre-stretch (% at break)	IPG/Highlight	383
Cling (in to out, grams at 200% pre-stretch)	IPG method	230 grams

While we believe them to be reliable, the statements and information herein are only for general guidance and are not warrants or guarantees for accuracy and completeness. The user must, by test or otherwise, determine suitability for this purpose. There is no warranty of fitness for a particular purpose. Our standard term and conditions of sale apply exclusively to all orders, and all liability for damages of any kind, including consequential, exceeding purchase price is excluded. No one is authorized by us to make oral warranties. We reserve the right to make changes without notice or obligation in our products and publications.



100 Paramount Drive, Suite 300 | Sarasota, FL 34232 | USA
 Customer Service: 888.898.7834
www.itape.com | info@itape.com

EFFECTIVE: 05/22/20

